



Dyckerhoff Weiss DW

Portland cement EN 197-1 - CEM I 42,5 R (dw)

data according EN 196

	standard values		requirements in EN 197-1
mechanical data:			
compressive strength: 2 days [MPa]	30	≥	20,0
compressive strength: 28 days [MPa]	57		42,5 - 62,5
physical data:			
water demand [%]	28		
setting time (initial) [min]	202	≥	60
Le Chatelier test [mm]	1	≤	10
chemical data:			
loss on ignition [%]	3,2	≤	5,0
insol. residue [%]	0,4	≤	5,0
sulphate content (SO ₃) [%]	3,0	≤	4,0

CEM I 42,5 R (dw) is produced, tested and certified acc. EN 197-1.

Certificat of conformity: 840-CPR-1210-130009-01

KOMO Certificat: 1138-1017-23.1

NF certifikat: 92.34 from 07.02.2024

Dyckerhoff GmbH, Werk Amöneburg
Biebricher Straße 74
65203 Amöneburg
Tel.:(0611) 676-2442

date: 16.04.2024
Gregor Guendisch