



## Dyckerhoff PKZ Doppel N

### Portland limestone cement EN 197-1 - CEM II/A-LL 42,5 N

data according to EN 196

	typical data		requirements in EN 197-1/DIN 1164-10
<b>mechanical data:</b>			
compressive strength 2 days [MPa]	28	≥	10,0
compressive strength 28 days [MPa]	49		42,5 - 62,5
<b>physical data:</b>			
water demand [%]	29		
setting time (initial) [min]	160	≥	60
Le Chatelier test [mm]	1	≤	10
<b>chemical data:</b>			
sulfate content (SO <sub>3</sub> ) [%]	3,1	≤	4,0

type of cement is produced, tested and certified acc. EN 197  
certificate of consistency of performance 0840-CPR-5410-246100-09  
Dancert certificate B 256-4

Dyckerhoff GmbH, Werk Deuna  
Industriestr. 7  
D-37355 Niederorschel  
Telefon: +49 (0)36076 8 2200

Datum: 20.08.2024  
gez. S. Stolze  
Quality assurance manager