



## Dyckerhoff PKZ Doppel R

### Portlandkalksteinzement EN 197-1 - CEM II/A-LL 42,5 R

Data according to EN 196

	Typical data	Requirements in EN 197-1
<b>Mechanical data:</b>		
Compressive strength 2 days [MPa]	35	≥ 20,0
Compressive strength 28 days [MPa]	56	≥ 42,5 / ≤ 62,5
<b>Physical data:</b>		
Water demand [%]	29	
Setting time (initial) [min]	147	≥ 60
Le Chatelier test [mm]	1	≤ 10
<b>Chemical data:</b>		
Loss on ignition [%]	7,6	keine
Sulfate content (SO <sub>3</sub> ) [%]	3,1	≤ 4,0

CEM II/A-LL 42,5 R is produced, tested and certified acc. EN 197-1.

Certificate of consistency of performance: 0840-CPR-1240-236100-01

KOMO Certificate: 1139-16-1056

Dyckerhoff GmbH, Werk Lengerich  
Postfach 1240 / 1260  
D-49525 Lengerich  
Telefon: +49 (0)5481 / 31-0

Datum: 26.01.2021  
Dr. Böttcher (Qualitätsbeauftragter)