



Dyckerhoff PKZ Doppel R

Portlandkalksteinzement EN 197-1 - CEM II/A-LL 42,5 R

Data according to EN 196

| | Typical data | Requirements in EN 197-1 |
|--|--------------|--------------------------|
| Mechanical data: | | |
| Compressive strength 2 days [MPa] | 35 | ≥ 20,0 |
| Compressive strength 28 days [MPa] | 57 | ≥ 42,5 / ≤ 62,5 |
| Physical data: | | |
| Water demand [%] | 29 | |
| Setting time (initial) [min] | 136 | ≥ 60 |
| Le Chatelier test [mm] | 1 | ≤ 10 |
| Chemical data: | | |
| Loss on ignition [%] | 8,2 | keine |
| Sulfate content (SO ₃) [%] | 3,0 | ≤ 4,0 |

CEM II/A-LL 42,5 R is produced, tested and certified acc. EN 197-1.

Certificate of consistency of performance: 0840-CPR-1240-236100-01

KOMO Certificate: 1139-1056-23.1

Dyckerhoff GmbH, Werk Lengerich
Postfach 1240 / 1260
D-49525 Lengerich
Telefon: +49 (0)5481 / 31-0

Datum: 07.02.2024
Dr. Böttcher (Qualitätsbeauftragter)