



Dyckerhoff PKZ Doppel N

Portlandkalksteinzement EN 197-1 - CEM II/A-LL 42,5 N

Data according to EN 196

	Typical data	Requirements in EN 197-1
Mechanical data:		
Compressive strength 2 days [MPa]	26	≥ 10,0
Compressive strength 28 days [MPa]	49	≥ 42,5 / ≤ 62,5
Physical data:		
Water demand [%]	27	
Setting time (initial) [min]	172	≥ 60
Le Chatelier test [mm]	1	≤ 10
Chemical data:		
Loss on ignition [%]	7,9	keine
Sulfate content (SO ₃) [%]	3,1	≤ 3,5

CEM II/A-LL 42,5 N is produced, tested and certified acc. EN 197-1.

Certificate of consistency of performance: 0840-CPR-1240-246100-18

KOMO Certificate: 1139-19-1053

BENOR: Reg.-Nr. 20/14/477

Dyckerhoff GmbH, Werk Lengerich
Postfach 1240 / 1260
D-49525 Lengerich
Telefon: +49 (0)5481 / 31-0

Datum: 03.01.2020
Dr. Böttcher (Qualitätsbeauftragter)