



Dyckerhoff EPZ Doppel

Portland-slag cement EN 197-1 - CEM II/B-S 42,5 N

data according to EN 196

	typical data		requirements in EN 197-1
mechanical data:			
compressive strength 2 days [MPa]	21	≥	10,0
compressive strength 28 days [MPa]	58		42,5 - 62,5
physical data:			
water demand [%]	28		
setting time (initial) [min]	210	≥	60
Le Chatelier test [mm]	1	≤	10
chemical data:			
loss on ignition [%]	2,0		
insoluble residue [%]	1,1		
sulfate content (SO ₃) [%]	3,1	≤	3,5

type of cement is produced, tested and certified acc. EN 197.

certificate of consistency of performance: 0840-CPR-1260-241200-15

Dyckerhoff GmbH, Werksgruppe Süd
Postfach 6
D-67307 Göllheim
Telefon: +49 (0)6351 / 71-0

Datum: 22.03.2022
Gündisch
Unterschrift