



Dyckerhoff PKZ Dreifach N

Portland Limestone Cement EN 197-1 - CEM II/A-LL 52,5 N

data according to EN 196

	typical data		requirements in EN 197-1
mechanical data:			
compressive strength 1 day [MPa]	18		
compressive strength 2 days [MPa]	30	≥	20,0
compressive strength 28 days [MPa]	57	≥	52,5
physical data:			
water demand [%]	30		
setting time (initial) [min]	230	≥	45
Le Chatelier test [mm]	1	≤	10
chemical data:			
loss on ignition [%]	6,0		
insoluble residue [%]	1,8		
sulfate content (SO ₃) [%]	3,1	≤	4,0

type of cement is produced, tested and certified acc. EN 197.

certificate of consistency of performance: 0840-CPR-1260-226100-23

Dyckerhoff GmbH, Werk Göllheim
Postfach 6
D-67307 Göllheim
Telefon: +49 (0)6351 / 71-0

Datum: 30.01.2024
Gündisch
Unterschrift