



Dyckerhoff EPZ Doppel

Hochofenzement EN 197-1 - CEM II/B-S 42,5 N

gegevens conform EN 196

	typisch waarden	eisen conform EN 197-1
mechanische gegevens:		
druksterkte 2 dagen [MPa]	22	≥ 10,0
druksterkte 28 dagen [MPa]	57	≥ 42,5 / ≤ 62,5
fysieke gegevens:		
waterbehoefte [%]	29	
begin binding [min]	177	≥ 60
vormhoudendheid (expansi) [mm]	1	≤ 10
chemische gegevens:		
gloeiverlies [%]	2,3	≤ 5,0
waarvan onoplosbaar [%]	1	≤ 5
sulfaat-gehalte (SO ₃) [%]	3,2	≤ 3,5

CEM II/B-S 42,5 N wordt geproduceerd, getest en gecertificeerd conform EN 197-1.

Certificate of consistency of performance: 0840-CPR-1270-241200-18