



## Dyckerhoff HOZ Doppel

### Blast Furnace Slag Cement EN 197-1 - CEM III/A 42,5 N (na)

Data according to EN 196

	Typical data	Requirements in EN 197-1
<b>Mechanical data:</b>		
Compressive strength 2 days [MPa]	14	≥ 10,0
Compressive strength 28 days [MPa]	54	≥ 42,5 / ≤ 62,5
<b>Physical data:</b>		
Water demand [%]	30	
Setting time (initial) [min]	184	≥ 60
Le Chatelier test [mm]	1	≤ 10
<b>Chemical data:</b>		
Loss on ignition [%]	2,7	≤ 5,0
Insoluble residue [%]	1	≤ 5
Sulfate content (SO <sub>3</sub> ) [%]	3,4	≤ 4,0
Na <sub>2</sub> O-equivalent [%]	0,7	≤ 0,95

CEM III/A 42,5 N (na) is produced, tested and certified acc. EN 197-1.

Certificate of consistency of performance: 0840-CPR-1270-340175-17

Product Certificate: 1270-340175-17

KOMO Certificate: 1140-16-1062

Dyckerhoff GmbH, Plant Lengerich  
Postbox 1240 / 1260  
D-49525 Lengerich  
Phone: +49 (0)5481 / 31-0

Date: 08.02.2024  
Dr. Böttcher (Quality assurance manager)