



## Dyckerhoff HOZ Doppel

### Hoogovencement EN 197-1 - CEM III/A 42,5 N (na)

gegevens conform EN 196

	typisch waarden	eisen conform EN 197-1
<b>mechanische gegevens:</b>		
druksterkte 2 dagen [MPa]	14	≥ 10,0
druksterkte 28 dagen [MPa]	54	≥ 42,5
<b>fysieke gegevens:</b>		
waterbehoefte [%]	30	
begin binding [min]	164	≥ 60
vormhoudendheid (expansi) [mm]	1	≤ 10
<b>chemische gegevens:</b>		
gloeiverlies [%]	2,7	≤ 5,0
waarvan onoplosbaar [%]	1	≤ 5
sulfaat-gehalte (SO <sub>3</sub> ) [%]	3,5	≤ 4,0
Na <sub>2</sub> O-equivalent [%]	0,8	≤ 0,95

CEM III/A 42,5 N (na) wordt geproduceerd, getest en gecertificeerd conform EN 197-1.

Certificate of consistency of performance: 0840-CPR-1270-340175-17

Product Certificate: 1270-340175-17

KOMO Certificate: 1140-16-1062

Dyckerhoff GmbH, fabriek Lengerich  
Postbus 1240 / 1260  
D-49525 Lengerich  
Telefoon: +49 (0)5481 / 31-0

Datum: 11.01.2022  
Dr. Böttcher (Manager kwaliteitszorg)