



Dyckerhoff TrZ Doppel

Portland-pozzolana cement EN 197-1 - CEM II/B-P 42,5 N

conformité selon EN 196

	typical data		requirements in EN 197-1
mechanical data:			
compressive strength 2 days [MPa]	32	≥	10,0
compressive strength 28 days [MPa]	55		42,5 - 62,5
physical data:			
water demand [%]	34		
setting time (initial) [min]	137	≥	60
Le Chatelier test [mm]	1	≤	10
chemical data:			
loss on ignition [%]	4,0		
insoluble residue [%]	3,6		
sulfate content (SO ₃) [%]	2,8	≤	3,5

CEM II/B-P 42,5 N is produced, tested and certified acc. EN 197-1.

Certificate of conformity: 0840-CPR-1290-243200-10

Dyckerhoff GmbH, Werksgruppe West
Postfach 14 43
D-56504 Neuwied
Telefon: +49 (0)2631/808-228

Datum: 25.11.2024
Gregor Gündisch