



## Dyckerhoff COMFORT

### Portland-limestone cement EN 197-1 - CEM II/A-LL 42,5 N

conformité selon EN 196

	typical data		requirements in EN 197-1
<b>mechanical data:</b>			
compressive strength 2 days [MPa]	29	≥	10,0
compressive strength 28 days [MPa]	51		42,5 - 62,5
<b>physical data:</b>			
water demand [%]	31		
setting time (initial) [min]	184	≥	60
Le Chatelier test [mm]	1	≤	10
<b>chemical data:</b>			
loss on ignition [%]	9,3		
insoluble residue [%]	1,2		
sulfate content (SO <sub>3</sub> ) [%]	3,1	≤	3,5

CEM II/A-LL 42,5 N is produced, tested and certified acc. EN 197-1.

Certificate of conformity: 0840-CPR-1290-246100-19

NF Certificate: 1022.08

KOMO Certificate: 1166-1053-19.1

Dyckerhoff GmbH, Werksgruppe West  
Postfach 14 43  
D-56504 Neuwied  
Telefon: +49 (0)2631/808-228

Datum: 25.11.2024  
Gregor Gündisch