



Dyckerhoff Comfort Dreifach FT

Portland-slag cement EN 197-1 - CEM II/A-S 52,5 R (ft)

data according to EN 196

	valeur typique		requirements in EN 197-1
mechanical data:			
compressive strength 2 days [MPa]	37	≥	30,0
compressive strength 28 days [MPa]	68	≥	52,5
physical data:			
water demand [%]	32		
setting time (initial) [min]	142	≥	45
Le Chatelier test [mm]	1	≤	10
chemical data:			
loss on ignition [%]	2,7		
insoluble residue [%]	0,6		
sulfate content (SO ₃) [%]	3,2	≤	4,0

CEM II/A-S 52,5 R (ft) is produced, tested and certified acc. EN 197-1.

Certificate of conformity: 0840-CPR-1290-211110-09

KOMO Certificate: 1166-16-1088

Dyckerhoff GmbH, Werksgruppe West
Postfach 14 43
D-56504 Neuwied
Telefon: +49 (0)2631/808-228

Datum: 25.11.2024
Gregor Gündisch