



Dyckerhoff Variodur 40

blast furnance cement EN 197-1 - CEM III/A 52,5 R

data according EN 196

	typical data		requirements in EN 197-1
mechanical data:			
compressive strength 2 days [MPa]	34	≥	30,0
compressive strength 28 days [MPa]	80	≥	52,5
physical data:			
water demand [%]	32		
setting time (initial) [min]	185	≥	45
Le Chatelier test [mm]	1	≤	10
chemical data:			
loss on ignition [%]	1,8	≤	5,0
insoluble residue [%]	1,3	≤	5,0
sulfate content (SO ₃) [%]	2,1	≤	4,0

CEM III/A 52,5 R is produced, tested an certified acc. EN 197-1.

Certificate of conformity: 0840-CPR-1290-310100-07

Dyckerhoff GmbH, Werksgruppe West
Postfach 14 43
D-56504 Neuwied
Telefon: +49 (0)2631/808-228

Datum: 25.11.2024
Gregor Gündisch